

Rammed earth

Item No. 02.004, 02.008, 02.100, 02.200, 02.400, 02.600

- Original and pure clay construction
- Fascinating appearance
- For walls and floors



Natural FINE
Item No. 02.008



Natural
Item No. 02.004



White
Item No. 02.100



Yellow
Item No. 02.200



Red
Item No. 02.400



Grey
Item No. 02.600

Rammed earth ready mix for walls and floors. Rammed earth construction is clay construction in its archaic and pure form. The raw material is directly formed into a monolithic construction element. The main reason that this ancient construction technique was rediscovered was because of the aesthetic and expressive power of the heavy monolithic components and their surfaces. Natural fine rammed earth is for covering rammed earth floors. The finer grain makes it easier to produce a floor surface. The compacted material can then be oiled or fixed and finished with wax.



GERMANY
© ClayTec GmbH & Co. KG
Nettetalter Straße 113-117
D-41751 Viersen-Boisheim
+49 (0)2153 918-0
service@claytec.com
claytec.com

2025/9
Changes and errors excepted.
Current version available at
claytec.com

Rammed earth

Item No. 02.004, 02.008, 02.100, 02.200, 02.400, 02.600

Application Type of clay product Rammed earth (STL) according to 3.2 of the "Clay building rules" of the Dachverband Lehm (German clay construction trade association).

Field of application Rammed earth for load-bearing and non-load-bearing clay walls that are not exposed to the weather. Fine rammed earth for clay floors.

Composition Building clay, mixed-grain stony additives. Grain size 0-16 mm (oversized grain up to 22 mm possible).
Fine rammed earth 02.008 grain size 0-8 mm (oversized grain up to 16 mm possible).

Material properties Dry bulk density approx. 2.300 kg/m³, thermal conductivity 1.5 W/mK, μ 5/10, building material class A1, compressive strength Natural rammed earth 2.0 N/mm², other rammed earth products on demand, drying shrinkage Natural rammed earth 0.5%.
Rammed earth White, Yellow, Red and Grey as well as Natural FINE rammed earth 0.7%.

Supply form Earth-moist in 1.0 t Big Bags

Storage Protect against dehydration (clumping together) or humidification by weather. Can be stored for long periods.
Check the moisture and homogeneity (workability) of the building material before starting work.

Material needs A Big Bag yields approx. 0.45 m³ of finished wall component.

Processing, execution Walls: The rammed earth is filled into sufficiently strong formwork in 100-150 mm thick layers and compacted evenly up to its maximum by hand or machine. **Load-bearing walls are planned and dimensioned in accordance with the "Clay building rules" of the Dachverband Lehm (German clay construction trade association). Walls may only be made under the instruction and supervision of an expert with sufficient experience in the construction of load-bearing clay building components.**

Floors: For application over concrete slabs, plan on a total thickness of at least 100 mm, and for application over soil or insulation (e.g. foam glass gravel), plan on a total application thickness at least 160 mm. Rammed earth is applied in layers onto a clean and rigid base and compacted evenly the maximum amount possible, by hand or machine. **Floors in which the tread surface is to be made of clay, can only be constructed by specialists experienced in the production of such floors.**

Drying The drying time depends on the installation thickness, season and weather. Subsequent processing may only be carried out after it has dried sufficiently.

Subsequent processing Building components are usually provided with protection against the weather. ClayTec clay undercoat plaster, clay topcoat plaster coarse or clay plaster mineral 20 are suitable interior plasters. They should be used in accordance with Worksheet "Clay plasters".
Floors: Uneven surfaces can be reworked with a trowel applying high pressure. Surface treatments with hard wax for floors or hard oil plus hard wax for floors improve the surface strength. **Test the effect first on a sample area.**

Notes Rammed earth is water-soluble and therefore not suitable for use as a weather skin. For deviating applications by specialist companies with experience in this field, please contact us separately.

Working with rammed earth requires a high level of knowledge and skill. We are happy to provide professional advice and assistance during the planning and execution.

Should additional moistening or homogenisation of the rammed earth become necessary, this will not be considered grounds for complaint.

Samples should always be prepared in order to assess the final appearance of the rammed earth. Because of naturally occurring differences in the color of the clay and additives, deviations in the color of rammed earth are not typically regarded as grounds for complaint. We undertake to ensure the best possible color consistency.

Damage caused by the weathering of non-plastered or clad surfaces is also not considered grounds for complaint.

Claims for compensation that do not result from factory mixing errors are excluded.
Subject to change and errors excepted. As of 2025/9.