

Lightweight clay insulation plaster

Item. No. 05.036, 05.236

- The clay basecoat classic
- Multi-functional
- Easiest to work with



Single or multilayer basecoat plaster for interior application. Why waste the space under your interior insulation boards? In comparison to normal clay plaster mortars, layers of clay insulation plaster reduce markedly improve the transport of heat through the wall. Clay insulation plaster is also a problem-solver for many other scenarios, e.g. for window soffits or minimal insulation focused on only certain areas. The plaster is suitable as a substrate for all coarse and fine ClayTec clay topcoat plasters.

ClayTec®

GERMANY
© ClayTec GmbH & Co. KG
Nettetalter Straße 113-117
D-41751 Viersen-Boisheim
+49 (0)2153 918-0
service@claytec.com
claytec.com

2025/10
Changes and errors excepted.
Current version available at
claytec.com

Lightweight clay insulation plaster

Item. No. 05.036, 05.236

Type of clay plaster mortar Clay plaster mortar for use as plastering mortar. Earth-moistened, 05.036 and 05.236.

Application Single or multilayer basecoat plaster for interior application. Hand-applied plaster. As a thick-layer levelling plaster beneath interior insulation boards, for uneven window soffits and conical plaster layers, on thermal bridges and connecting walls and ceilings, for patched minimal insulation.

Composition Natural clay up to 5 mm, pumice 1–5 mm, sand 0–2 mm, straw 10 mm, cellulose

Country of origin Germany

Material properties Bulk density 1,000 kg/m³. Thermal conductivity 0.35 W/m·K. μ value 5/10. Building material class B2*. Microbial quality class MBKIIb (analogous to DIN 18947).

Supply form, coverage

Earth-moistened 05.036 in 0.9 t Big Bags (yields 720 l plaster mortar, 48 m² area at thickness = 1.5 cm. Approx. 1.25 kg/m² per mm plaster thickness).
Earth-moistened 05.236 in 0.45 t Big Bags (yields 360 l plaster mortar, 24 m² area at thickness = 1.5 cm. Approx. 1.25 kg/m² per mm plaster thickness).

Storage Store in a dry place. Earth-moist lightweight clay insulation plaster should be applied no later than 3 months after manufacture. In winter, earth-moist goods must be stored so they are protected from freezing, otherwise workability during frost is impaired.

Mortar preparation With the addition of approx. 20 % water using commonly available rotary drums, turbomixers and pug mill mixers. In small quantities may also be mixed with a power agitator or by hand.

Plaster base Clay plasters adhere only by mechanical force. The substrate must be stable, frost-free, dry, clean, free of salt, sufficiently rough and absorbent. If necessary, a suitable primer is RED for coarse clay plasters (ClayTec 13.435–.430). **If necessary, the substrate may be moistened first (with a spray) to bind surface dust. Reed matting must be dry. Remove any previous coatings that form a film.**

Plaster application method The mortar is thrown or applied with a trowel. Minimum and maximum application thickness usually 8 and 15 mm. The consistency of the mortar must be matched to the application thickness. The apply YOSIMA clay designer plasters, the surfaces are prepared with a layer of clay topcoat fine 06.

Working time Since no chemical setting process takes place, the material remains workable for several days if kept covered.

Drying After application, it is essential to ensure that drying takes place rapidly, e. g. by means of cross-ventilation (all windows and doors kept open 24 hours a day) or drying equipment. Under critical conditions, drying must be documented in accordance with DIN 18550-2. Details can be found there or in the ClayTec 'Clay plasters worksheet'. We will be happy to provide separate information. The basic microbiological contamination of Naturally-moist goods 05.036 and 05.236 is subject to continuous monitoring; compliance with certain values cannot be guaranteed.

Subsequent plastering Subsequent plastering is carried out after complete drying, at the earliest after completion of possible shrinkage crack formation.

Sample application In all cases, the suitability of the primer and thickness of application must be tested by means of a sample application of sufficient area.

Claims for compensation that do not result from factory mixing errors are excluded.
Subject to change and errors excepted. As of 2025/10.

*Better classification is possible subject to fire protection tests (Lehmbau Regeln DVL 2009, p. 97).